



Product Information Demotex S 1000

Description	Thin release agent to spray on mould pattern or core boxes. Demotex S 1000 is a dispersion of active substances in a solvent mixture.										
Field of use	Moulding and core shop. Demotex S 1000 is applicable to all common cold curable core and mould making processes, particularly to hand moulding.										
Application	Demotex S 1000 is to use undiluted in supply condition after it was stirred. The release agent should be sprayed thinly and evenly on the clean pattern surface. The processing is done by brushing or spraying by hand. Prior to using the form the flashing off / drying off of the release film is required. If used properly, a multiple demoulding of mould or core is possible.										
Technical data	<table> <tr> <td>Colour:</td> <td>silver grey</td> </tr> <tr> <td>Active substance:</td> <td>aluminium pigments</td> </tr> <tr> <td>Density (20 °C):</td> <td>approx. 0,8 g/cm³</td> </tr> <tr> <td>Viscosity (23 °C):</td> <td>approx. 30 s</td> </tr> <tr> <td>Flash point:</td> <td>< 21 °C</td> </tr> </table>	Colour:	silver grey	Active substance:	aluminium pigments	Density (20 °C):	approx. 0,8 g/cm ³	Viscosity (23 °C):	approx. 30 s	Flash point:	< 21 °C
Colour:	silver grey										
Active substance:	aluminium pigments										
Density (20 °C):	approx. 0,8 g/cm ³										
Viscosity (23 °C):	approx. 30 s										
Flash point:	< 21 °C										
Packaging	<u>Can á 18 kg</u>										
Storage	Store Demotex S 1000 tightly closed and frost-free in a dry, well-ventilated place; protect from heat and direct sunlight. Shelf life 6 months when properly stored inside in original unopened container.										
Regulations and information	Demotex S 1000 is classified and labeled according to the CLP regulation and corresponds to the current EC regulation. Information about transport regulations, fire-fighting measures, accidental release, ecology and further information can be found in the material safety data sheet.										

All information in this data sheet are based on our current knowledge and experience. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived. Each user of our products has to verify the usability for its specific purpose in his personal responsibility. Rights must be observed if required.

HN/MT

status 06/15